

RECEIVED


9. (Amended) Method according to any one of Claims 4 to 8, characterized in that

the said grafted silicone polymer is capable of being obtained by radical polymerization from

the mixture of

TECH CENTER 1500/2500


[



]

monomers consisting of:

- a) 60 weight % of *tert*-butyl acrylate;
- b) 20 weight % of acrylic acid;
- c) 20 weight % of silicone macromer of formula (III):



with n being a number ranging from 1 to 700, the percentages by weight being calculated

with respect to the total weight of the monomers.